

Basic Quality Statistical Summary Report

GRADATIONS

POROUS CONCRETE SIDEWALK

Product GADOT 89

Sieve/Test	Tests	Average	St Dev	Target	Specification
1/2" (12.5mm)	19	100.0	0.00	≥100	100-100
3/8" (9.5mm)	19	99.9	0.16	93-100	90-100
#4 (4.75mm)	19	39.3	4.17	23-43	20-55
#8 (2.36mm)	19	7.6	2.58	0-7	0-15
#16 (1.18mm)	19	3.5	1.32	0-5	0-10
#50 (.3mm)	19	1.4	0.77	0-1	0-5
Pan	19	0.00	0.000		
FM	19	5.45	0.092		

NOTE: High Range Water Reducer to be utilized and must comply with the Specifications for Chemical Admixtures for Concrete, ASTM: C494 Type A, F and ASTM C1017, AASHTO: M194, Type A, F.